

Permeable Driveway (SuDS) using 'Cellweb'TM

Typical base build up using a Cellular Confinement System

Recommended specification for Addaset, Addaset Ecolife and Addaset Amber:

0.5mm diameter glass grit lightly broadcasted onto uncured surface for antislip.

Surface Course

Hand applied and trowelled to a smooth finish by Addagrip approved installers. An aggregate size of 6mm or 10mm requires a 45mm depth.

Sub-base


Laid by others in well compacted layers to a minimum fall of 1.5% (1 in 66) A 125mm depth of well compacted, non-frost susceptible Type 3 granular sub-base to SHW clause 805 or 4/40mm, 4/20mm graded crushed concrete aggregate to BS EN12620 or locally available secondary or recycled aggregates which comply with the requirements of the specifications for Highway works for sub-bases in conjunction with a 100mm deep 'Cellweb'TM or similar standard cellular confinement blanket and a 25mm surcharge.

Optional membrane Sub-grade

A 'Cellweb'TM fibretex F4M Geotextile Separation fabric' to prevent upward migration of fine soil particles (optional).

Sub-grade

CBR>5% required. If below, capping layers required to strengthen soil.



Note:

Suitable steel, wood, brick, stone or aluminum edging should be provided to ensure a neat detail. The maximum tolerance of the base should not exceed 3mm under a 1m straight edge.

If plastic or silty sub-grade is present, a capping layer should be used in accordance with HA Design Manual for Road and Bridges HD25.

If there is a danger of ponding, the sub-base should be laid to falls.

Total sub-base thickness will be dictated by loading and attenuation requirements.

Any advice, recommendation or information given by Addagrip Terraco Ltd is based on practical experience and is believed to be accurate at the time of publication. No liability or responsibility of any kind (including liability for negligence) is accepted in this respect by the company, its Servants or Agents.

The figures quoted do not constitute a specification, they represent typical values obtained for this product.